ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

BOPP PLAIN FILM

Test report (Tech data)

Standard : GB/T1003-96。

1、machinability

Items	Prime	Eligible	Weak	Test method	Marking
Tensile strength in machine	MD	GB13022-91	≥150	≥120	
	TD		≥260	≥260	
Elongation in machine	MD	GB13022-91	≤180	≤180	
	TD		≤65	≤65	
elasticity（Three days later）Mpa		GB13022-91	≥1700	≥1700	
Thermal contraction %	MD	GB/T1003-96	≤4	≤5	
	TD		≤2	≤3	
Haze %		GB2410-80	≤1.2	≤1.5	
Transparency stability %		GB2410-80	≥85	/	
Gloss %		GB8807-88	≥90	≥85	
Wettability mN/m		GB/T14216-93	≥39	≥38	
Fraction coefficient %	MD	GB/10006-88	≤0.8	≤0.8	
	TD		≤0.8	≤0.8	

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

2、Dimension

Items	Prime	Eligible	Weak
Dimensional Stability	±3.0%	±4.5%	±7.0%
Averagabal DimensionalStability	±2.5%	±4.0%	/
Length Stability	＜30um ±300 M	±800 M	/
	≥30um ±150M	±400M	/
The length of junction	＜20um ＞1000M	＞500M	/
	20~30um ＞800M		
	＞30um ＞500M		
Width Stability	≤±2mm	＞±2mm	/

3、Appearance

Items	Prime	Eligible	Weak	Test method	Marking
Damage of core	NO	NO	YES	BY SIGHT	O
Damage of edge	NO	A LITTLE	BADLY	BY SIGHT	B
Joint	NO	One joints is allowed	3 jionts	BY SIGHT	J

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

deflection	≤1mm	≤3mm	>3mm	BY RULE	P
Warp on eldge	NO	NO	Obviously	BY SIGHT	G
Dent	NO	NO	/	BY SIGHT	V
Color distinction	NO	Obviously	/	BY SIGHT	D
Bruise	NO	Obviously	Obviously	BY SIGHT	R
Contamination	NO	NO	/	BY SIGHT	W
Balloon	Diameter <0.5mm One or two, diameter<0.5mm three	Yes	/	BY SIGHT	K
Material leakage	NO	Lightly	Badly	BY SIGHT	H
Dyne distinction	≥38	≥36			U
Damage	No	Lightly	Badly		X
Width	±1	±2			A
Length distinction	Do as clients	Light distinction	Badly	BY COMPUTER	C

4、Roll's quality

Items	Prime	Eligible	Weak	Test method	Marking

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Dent	**Width below 1000mm ⩽50m Width above 1000mm ⩽100m**	**⩽250m**	**/**	**BY SIGHT**	**F**
Dent inside	**No**	**No**	**> 300m**	**BY SIGHT**	**L**
Longitudinal marking	**NO**	**No**	**/**	**BY SIGHT**	**T**
Traversenal marking	**NO**	**No**	**/**	**BY SIGHT**	**M**
Blotch	**No**	**Lightly**	**/**	**BY SIGHT**	**Q**