ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

Name of the Product	
Product	Bioriented Polipropilen Film
Common Name	BOPP 35 micron
Tech Name	Clear Polipropilen

Description of the Product

Bi-axially Oriented Polypropylene (BOPP) film, co-extruded, clear (transparent), with a good gloss and clarity, for high speed machines with fine sliding, smoothness and antistatic. Two side sealable and corona-treated in one face for printing and laminating by adhesion. For packaging Pasta; FDA compliant for contact with food.

Product Identification and Handling

1. The product must be delivered in rolls; in plataforms and protected by walls; surrounded with strech polyethylene; there has to be no pollution agents present.
2. Each roll must have an identification label, containing: name of the supplier, type of product, lot, thickness, wide, and the face that has the treatment.
3. Each lot must have it's quality certificate.
4. The cores must have 6 inch diameter
5. The external diameter of the rolls must be 730 mm maximum with 1 or 2 rolls per reinforced plataform.

Technical Specifications

Property	Unit	Max.	Objective	Min.	Method	Criticity
Unit weight	g/m2	32.7	31.5	30.3	II-7.4-CJ-04	Critic
Thikness	micron	36.8	35	33.7	II-7.4-CJ-05	Critic
Performance	m2/kg	32.9	31.7	30.5	II-7.4-CJ-04	Critic
Resistance to Tension (break) DM/DT	Lb/inch2	23060.90 46267.02	18790.4 38434.99	14520.0 30602.95	ASTM-D882 II-7.4-CJ-03	Great
Resitance to Elongation DM/DT	%	300 / 100	150 / 70	107 / 31	ASTM-D882 II-7.4-CJ-03	Great
Superficial Tension or Treatment Level	Dinas	---	---	38	ASTMD2578 II-7.4-CJ-01	Critic
Dynamic coefficient of Friction PNT/PNT; PNT/MET	---	0.45/0.32	0.30/ 0.21	0.15/0.10	ASTMD1894 II-8.2-CJ-02	Critic
Temperature for Sealing initiation	°C	---	120	---	II-8.2-CJ-18	Great
Seal resistance @ 60 psi; 0.5 seg.	Lb/inch2	---	---	0.44	II-8.2-CJ-18	Great
Flatness / Curvature	mm	3	0	0	II-8.2-CJ-10	Critic

Special Notes

1. Supplier must not change any property or specification without written autorization.
2. The specificatoin for this product cancel any past specifications.
3. Not conforming with this data sheet will cause the rejection of the product.

Asia Pacific Industry Group Co., Limited
http://www.boppfilmsales.com
Skype:asiapacificfilm
Wechat/whatsapp/mobile:86-18919654871
AnHui Eastern Communication Chemicals
http://www.boppfilmsales.com

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 营业执照注册号 Business License Reg. No.: 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393