ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

PRODUCTNAME HAND STRETCH FILM

SPECIFICATION 23MIC*50CM*1500M

PHYSICAL PROPERTIES		UNIT	WRAP FILM
THICKNESS		mic	23mic
SPECIFIC GRAVITY		——	0.9188
MAXIMUM FORCE VALUE	MD	n	8.39
	CD		4.87
	Anti-pierce		5.57
DEFORMATION	MD	mm	166.55
	CD		332.73
	Anti-pierce		27.95
TENSILE STRENGTH	MD	mpa	8.39
	CD		4.87
	Anti-pierce		5.57
ELONGATION	MD	%	412.10
	CD		665.46
	Anti-pierce		55.90
YIELD STRENGTH	MD	mpa	0.97
	CD		0.81
	Anti-pierce		1.46
EPIGASTRIC LENGTH	MD	mm	216.55
	CD		382.73
	Anti-pierce		77.95
BREAKING STRENGTH	MD	mpa	3.26
	CD		1.87
	Anti-pierce		2.13
FRACTURE FORCE VALUE	MD	n	3.26
	CD		1.87
	Anti-pierce		2.13

地址 ADD.: No.3399, Luzhou Ave., Baohe Dist., Hefei, Anhui 230051, China | 安徽省合肥市包河区庐州大道3399号
传真 Fax: +0086-551-64683490 **营业执照注册号 Business License Reg. No.:** 91340100575703313N
海关注册编码 Customs Reg. Code: 3401961393

ASIA PACIFIC INDUSTRY GROUP CO., LIMITED
Tel +0086-551-64687285
Email sales@boppfilmsales.com
www.boppfilmsales.com · www.apigcl.com

检测报告单 Test report

品　名 Name	PE FILM		规　格 Specifications	320mm*80mic
抽样日期 Sample　Date	2018-12-27		检验依据 Test　Basis	
生产编号 Manufacture No.			生产日期 Date of manufacture	
检测结果 Testing　Vesult				
检验项目 Test　Propertiers		单位 Units	测试值 Test　Datas	单项结论 Single Conclusion
宽度 Width		mm	320mm	qualified
厚度 Thickness		um	80um	qualified
厚度偏差(max) Thickness Deviation		%	5%(8C)	qualified
拉伸强度 Tensile Strengtion	MD	Mpa	16.5	qualified
	TD		17	qualified
断裂伸长率 Elongation at Breat	MD	%	350	qualified
	TD		510	qualified
热封强度 1kgf/cm^2,1s Heat-sealing strength	130℃	N/15mm	8.5	qualified
摩擦系数 Friction Coefficient	u_s	–	/	qualified
	u_k		0.2	qualified
润湿张力 Wetting Tension		mN/m	38 达因	qualified
雾度 Haze		%	/	qualified
铝层厚度 Thickness of Aluminum Layer			/	qualified
铝层附着力 Firm of Aluminum Layer			/	qualified
外观 Apperance		qualified		
检验结论 Testing Conclusion		qualified		
备注 Notes				